

Superlight bipolarons and criterion of BCS-BEC crossover in cuprates

A. S. Alexandrov¹

¹*Department of Physics, Loughborough University, Loughborough LE11 3TU, United Kingdom*

Most of the proposed models of high-temperature superconductivity (HTSC) are based on the short-range electron-electron correlations or/and on a short-range electron-phonon interaction. However, in the cuprates the screening is poor due to a low carrier density, layered crystal structure, and high ionicity of the lattice. We develop further the bipolaron model of HTSC, which explicitly takes into account the long-range origin of all interactions. The long-range electron-phonon (Froehlich) interaction binds carriers into real space pairs (small bipolarons) with surprisingly low mass but sufficient binding energy, while the long-range Coulomb repulsion keeps them from forming larger clusters. The model has explained many key features of cuprates. It is shown here that real-space pairing takes place in many cuprates at variance with some (incorrect) criteria of the BCS-BEC crossover.

I. INTRODUCTION: BIPOLARON MODEL OF CUPRATES

The electron-phonon interaction as an origin of high T_c continues to gather support through isotope effect measurements, infrared, tunnelling, neutron and photoemission spectroscopies¹. To account for high values of T_c in the cuprates, it is necessary to have a strong electron-phonon interaction, when a many-electron-phonon system collapses into the small (bi)polaron regime². At first sight these carriers have a mass too large to be mobile, however it has been shown that the inclusion of the on-site Coulomb repulsion leads to the favoured binding of intersite oxygen holes³. The intersite bipolarons can then tunnel with an effective mass of only 10 electron masses^{3,4,5}.

Mott and the author proposed a simple model⁶ of the cuprates based on bipolarons, Fig.1. In this model all the holes (polarons) are bound into small intersite singlet and triplet bipolarons at any temperature. Above T_c this Bose gas is non-degenerate and below T_c phase coherence (ODLRO) of the preformed bosons sets in, followed by superfluidity of the charged carriers. The model accounts for the crossover regime at T^* and normal state pseudogaps in cuprates⁷. Here I show that real-space pairing takes place in many cuprates.

II. PAIRING IS 'INDIVIDUAL' IN MANY CUPRATES

The possibility of real-space pairing, as opposed to BCS-like pairing, has been the subject of much discussion. Experimental and theoretical evidence for an exceptionally strong electron-phonon interaction in high temperature superconductors is now so overwhelming, that even advocates of nonphononic mechanisms⁸ accept this fact. Nevertheless the same authors⁸ dismiss any real-space pairing claiming that pairing is collective in cuprates. They believe in a large Fermi surface with the number of holes $(1+x)$ rather than x , where x is the doping level like in $La_{2-x}Sr_xCuO_4$. As an alternative to a three-dimensional BEC of bipolarons these authors

suggest a collective pairing (i.e the *Cooper* pairs in the momentum space) at some temperature $T^* > T_c$, but without phase ordering. In this concept T_c is determined by the superfluid density, which is proportional to doping x , rather than to the total density of carriers $(1+x)$. On the experimental side a large Fermi surface is clearly incompatible with a great number of thermodynamic, magnetic, and kinetic measurements, which show that only holes *doped* into a parent insulator are carriers in the *normal* state. On the theoretical ground this preformed *Cooper*-pair (or phase-fluctuation) scenario contradicts a theorem⁹, which proves that the number of supercarriers (at $T = 0$) and normal-state carriers is the same in any *clean* superfluid.




FIG. 1: Bipolaron picture of high temperature superconductors. *A* corresponds to the singlet intersite bipolaron. *B* is the triplet intersite bipolaron, which naturally includes the addition of an extra excitation band. The crosses are copper sites and the circles are oxygen sites. w is the half bandwidth of the polaron band, t is the half bandwidth of the bipolaron band, $\Delta/2$ is the bipolaron binding energy per polaron and J is the exchange energy per bipolaron.

Here I show that objections against real-space pairing

also contradict a parameter-free estimate of the Fermi energy¹⁰. In cuprates the band structure is quasi-two-dimensional (2D) with a few degenerate hole pockets. Applying the parabolic approximation for the band dispersion we obtain the *renormalized* Fermi energy as $\epsilon_F = \hbar^2 \pi n_i d / (m_i^*)$, where d is the interplane distance, and n_i, m_i^* are the density of holes and their effective mass in each of the hole subbands i renormalized by the electron-phonon (and by any other) interaction. One can express the renormalized band-structure parameters through the in-plane magnetic-field penetration depth at $T \approx 0$, measured experimentally: $\lambda_H^{-2} = 4\pi e^2 \sum_i n_i / (m_i^* c^2)$. In the framework of the BCS theory this expression is applied to any *clean* superfluid, where m_i^* and n_i are the *normal* state mass and density of carriers, respectively. As a result, we obtain a *parameter-free* expression for the “true” Fermi energy as

$$\epsilon_F = \frac{\hbar^2 d c^2}{4 g e^2 \lambda_H^2}, \quad (1)$$

where g is the degeneracy of the spectrum which might depend on doping in cuprates. Because Eq.(1) does not contain any other band-structure parameters, the estimate of ϵ_F using this equation does not depend very much on the parabolic approximation for the band dispersion.

Parameter-free estimates of the Fermi energy using Eq.(1)¹⁰ show that the renormalised Fermi energy in many cuprates is certainly well below 100 meV and the pairing is individual. Indeed such pairing will occur when the size of a pair, ρ is smaller than the inter-pair separation, r . The size of a pair is estimated as $\rho = \hbar / (\sqrt{m^* \Delta})$, where Δ is the binding energy. Separation of pairs is directly related to the Fermi energy in 2D $r = \hbar \sqrt{\pi / (\epsilon_F m^*)}$. We see that the true condition for real-space pairing is

$$\epsilon_F \lesssim \pi \Delta \quad (2)$$

The bipolaron binding energy is thought to be twice the pseudogap. Experimentally measured pseudogap of many cuprates⁷ is as large as $\Delta/2 \gtrsim 50 \text{ meV}$, so that Eq.(2) is well satisfied in underdoped and even in a few optimally and overdoped cuprates. One should notice that the coherence length in the charged Bose gas has nothing to do with the size of the boson as erroneously assumed by some authors⁸. It depends on the interparticle distance and the mean-free path, and might be as large as in the BCS superconductor. Hence, it is incorrect to apply the ratio of the coherence length to the inter-carrier distance as a criterion of the BCS-Bose liquid crossover. The correct criterion is given by Eq.(2).

¹ For recent results see G. Zhao, M.B. Hunt, H. Keller and K.A. Muller, Nature, **385**, 236 (1997); A. Lanzara, P.V. Bogdanov, X.J. Zhou, S.A. Kellar, D.L. Feng, E.D. Lu, T. Yoshida, H. Eisaki, A. Fujimori, K. Kishio, J.I. Shimoyana, T. Noda, S. Uchida, Z. Hussain and Z.X. Shen, Nature, **412**, 510 (2001)

² A.S. Alexandrov, Phys. Rev. B, **46**, 2838 (1992).

³ A.S. Alexandrov, Phys. Rev. B, **53**, 2863 (1996).

⁴ J. Bonca J and S.A. Trugman, Phys. Rev. B **64**, 094507 (2001).

⁵ A.S. Alexandrov and P.E. Kornilovitch, J. Phys. :Con-

densed Matter **14**, 5337 (2002).

⁶ A.S. Alexandrov and N.F. Mott, J. Supercond (US), **7**, 599 (1994).

⁷ D. Mihailovic, V.V. Kabanov, K. Zagar, and J. Demsar, Phys. Rev. B **60**, 6995 (1999) and references therein.

⁸ E. W. Carlson, V. J. Emery, S. A. Kivelson, and D. Orgad, cond-mat/0206217 and references therein.

⁹ A. J. Leggett, Physica Fennica **8**, 125 (1973); J Stat. Phys. **93**, 927 (1998);

¹⁰ A.S. Alexandrov, Physica C **363**, 231 (2001).